

NewTechWood Ltd.


TEST REPORT

REPORT NUMBER
191220157GZU-001

FIRST ISSUE DATE
2020/1/10

REVISED DATE
2020/3/17

PAGES
4



Test Report

Issue Date: 2020/3/17 Intertek Report No. 191220157GZU-001

Applicant: NewTechWood Ltd.
Applicant Address: 19111 Walden Forest Dr. Suite B Humble, Tx 77346, USA
Attn: Cliff Lam
Manufacturer: HUIDONG MEIXIN PLASTIC LUMBER PRODUCTS MANUFACTURING CO.,Ltd
Manufacturer Address: NGA INDUSTRIAL PARK, DALING, HUIDONG, GUANGDONG PROVINCE, PRC
Attn: Qinghai Li

SUBJECT: Performance testing
<<NewTechWood UltraShield>>

Dear Sir,

This test report for represents the results of our evaluation of the above referenced product(s) to the requirements contained in the following standards:

TEST METHODS AND STANDARDS		
Refer to the next following Pages.		
SAMPLE ID	MODEL	SPECIFICATION
S191220157-001	NewTechWood UltraShield UH02 H1 treatment	138.00*22.50mm

SAMPLE RECEIVED: 2020/2/24
TESTED FROM: 2020/2/25 TO 2019/3/12

Test lab address: Room 4103 & 4203, No. 63, Punan Road, Huangpu District, Guangzhou,
Guangdong Province, China

This report is for the exclusive use of Intertek's Client and is provided pursuant to the agreement between Intertek and its Client. Intertek's responsibility and liability are limited to the terms and conditions of the agreement. Intertek assumes no liability to any party, other than to the Client in accordance with the agreement, for any loss, expense or damage occasioned by the use of this report. Only the Client is authorized to permit copying or distribution of this report and then only in its entirety. Any use of the Intertek name or one of its marks for the sale or advertisement of the tested material, product or service must first be approved in writing by Intertek. The observations and test results in this report are relevant only to the sample tested. This report by itself does not imply that the material, product, or service is or has ever been under an Intertek certification program. All the tests results give the statement of conformity refer to the decision rule of "Procedure 2 "Accuracy Method" as stated in the IEC Guide 115:2007.

Test Report

Issue Date: 2020/3/17

Intertek Report No. 191220157GZU-001

Test Items, Method and Results:

If related to subcontract, the remark* for the test items conducted by a subcontractor.

When determining the test result, measurement uncertainty has been considered.

No.	Test Item	Test Parameter	Test Result	Verdict
1	Appearance	Test method: refer to Clause 6.1 of EN 15534-1:2014+A1:2017	No defects found on the sample	—
2	*Anti-slip property-Ramp test	Test method: DIN 51130: 2014 Test direction: Only cross lengthwise direction. Classification: Classify the anti-slip property according to Table 1 below.	Corrected mean overall acceptance angle α_{ges} : 12.6° Slip resistance class: R10	—

Table 1- Slip-resistance classification based upon the corrected mean overall acceptance angle


Corrected mean overall acceptance angle α_{ges}	Slip resistance class
6° up to 10°	R9
over 10° up to 19°	R10
over 19° up to 27°	R11
over 27° up to 35°	R12
over 35°	R13

Test Report

Issue Date: 2020/3/17

Intertek Report No. 191220157GZU-001

APPENDIX: SAMPLE RECEIVED PHOTO



REPORT AUTHORIZED

When signed with physical or electronic signature, the contents of this report have been prepared and approved per Intertek's quality process in accordance with ISO 17025.

Approved by:

Prepared by:

Kelming Wang

Hanna Deng

Name: Kelming Wang
Title: Senior Project Engineer

Name: Hanna Deng
Title: Engineer

Revision:

Report NO.	DATE	Revision Reason	Revision Summary	AUTHOR	REVIEWER
191220157GZU-001	2020/1/10	/	First issue	Hanna Deng	Kelming Wang
191220157GZU-001	2020/3/17	According to client's requirements	Retest on the specified surface and direction	Hanna Deng	Kelming Wang

End of Test Report